

B2
4. (Twice Amended) The composite material according to claim 3, wherein the weight ratio of the aggregate component to the fine particle component is 1/10 to 10/1.

B3
6. (Twice Amended) The composite material according to claim 1, wherein the main component of the organic component is a curing resin.

B4
7. (Twice Amended) The composite material according to claim 6, wherein the main component resin of the organic component is a methacrylate resin.

8. (Twice Amended) The composite material according to claim 6, wherein the organic component contains a plasticizer.

9. (Twice Amended) The composite material according to claim 6, wherein the resin is contained by 6 to 15% by weight with respect to the total amount.

B5
17. (Twice Amended) The composite material according to claim 1, wherein the main component of the organic component is a methacrylate resin, to be cured by a combination of a polymethacrylate and at least one member selected from the group consisting of a methacrylate monomer, and an acrylate monomer.

18. (Twice Amended) The composite material according to claim 17, wherein the polymethacrylate is a polymethyl methacrylate, the methacrylate monomer and the acrylate monomer is one selected from the group consisting of a methyl methacrylate, an ethylhexyl methacrylate, and an ethylhexyl acrylate.